


# MARBLE



# *QUARRIES*





# Kavaklıdere Products



**CUDILLERO WHITE**



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,69 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,2 (By Weight)	740 (Kgf/cm <sup>2</sup> )	116 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,11	0,13	55,40	1,25

# CUDILLERO WHITE




## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,69 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,2 (By Weight)	740 (Kgf/cm <sup>2</sup> )	116 (Kgf/cm <sup>2</sup> )

# ASTURIAS WHITE

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,22	0,06	55,75	0,52



**ASTURIAS WHITE**



**ALBARRACIN WHITE**






## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,69 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,2 (By Weight)	740 (Kgf/cm <sup>2</sup> )	116 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,11	0,13	55,40	1,25

# ALBARRACIN WHITE



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,69 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,2 (By Weight)	740 (Kgf/cm <sup>2</sup> )	116 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,22	0,06	55,75	0,52

# TERVEL



**TERVEL**





# Kommersan Products



## Physical, Mechanical and Technological Specifications

Hardness Unit	Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

# PAMPANEIRA



PAMPANEIRA



GRENADA





## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,15	0,07	56,30	0,81

# GRENADA



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,15	0,07	56,30	0,81

# STUPA



Stupa



NEVADA



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm3)	2,71 (gr/cm3)	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

# NEVADA

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,15	0,07	56,30	0,81



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
3 (Mohs)	2,7 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,08(By Weight)	0,11 (By Weight)	156 (Kgf/cm <sup>2</sup> )	119 (Kgf/cm <sup>2</sup> )

# GIRONA

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
2,81	0,10	52,90	1,40



**GIRONA**







## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
3 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,72 (gr/cm <sup>3</sup> )	0,08 (By Weight)	0,11 (By Weight)	156 (Kgf/cm <sup>2</sup> )	119 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
2,81	0,10	52,90	1,40

# BESALU



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,14	44	55,49	0,30

This product can be sold as a French pattern set.

# ZAMORA



ZAMORA



**CASTRO**



## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

# CASTRO



## Physical, Mechanical and Technological Specifications

Hardness Unit	Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

# SANABRIA



**SANABRIA**



**ALTAMIRA**





## Physical, Mechanical and Technological Specifications

Hardness	Unit Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm3)	2,71 (gr/cm3)	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

## Chemical Specifications

SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	CaO	MgO
0,21	0,10	57,10	0,24

# ALTAMIRA



## Physical, Mechanical and Technological Specifications

Hardness Unit	Volume Weight	Density	Water Absorption at Atmosphere Pressure	Water Absorption at Boiling Water	Compressive Strength	Ratio of Fullness
2,7 (Mohs)	2,71 (gr/cm <sup>3</sup> )	2,71 (gr/cm <sup>3</sup> )	0,1 (By Weight)	0,04 (By Weight)	701 (Kgf/cm <sup>2</sup> )	48,7 (Kgf/cm <sup>2</sup> )

# MORELLA



**MORELLA**





Mersin

Products



**TENERIFE**




**TENERIFE**



COSTELLON







ALQUEZAR






Flawless  
Texture



# Excellent Surface



# ABOUT US

Our company, which started its operations in 2021, is Turkey's largest modern export company.

Izem Ltd specialises in supplying a varied range of high quality bathroom, home products into the retail, wholesale and construction industry all across the US & Europe & UK.

We have an innovative approach to developing our products that are competitive in the industry, as well as consistently ensuring we are up to date with the latest moving trends.

Professionalism, care and constant commitment to production processes, combined with close attention to the customer and the market, make our group an international company that is able to offer targeted and reliable solutions.

## **İzem Isı ve İnşaat Malzemeleri Dış Ticaret Ltd.Şti.**

### **Management Office**

75.Yıl Mahallesi

Bahri Sarıtepe Caddesi

No:51 -K:2 D:3

Yunusemre / Manisa /TURKEY

### **Head Office**

Cumhuriyet Mah.5050 Sok.No:3/55

Yunusemre /Manisa /TURKEY

**E-mail:** [info@izemexport.com](mailto:info@izemexport.com)